Zeolite-A Natural Mineral for Sustainable Agriculture

Sandip Kumar Gautam[1]*, Suneel Kumar[2] and Sandeep Kumar[3]

[1,2]SMS: Soil Science and Seed Technology, [3]Senior Scientist and Head,
KVK, Bahraich-II, ANDUAT, Kumarganj, U.P.

Corresponding Author
Sandip Kumar Gautam
Email: gauthamkumar97344@gmail.com

OPEN ACCESS

Keywords

Zeolite, Aluminosilicate, Molecular Sieve, Microporous Material, Adsorption, Hydrothermal Synthesis.

How to cite this article:

Gautam, S. K., Kumar, S. and Kumar, S. 2026. Zeolite-A Natural Mineral for Sustainable Agriculture. *Vigyan Varta* 7 (11): 86-95.

ABSTRACT

Zeolites are crystalline micro porous aluminosilicate materials that have become indispensable in modern science and industry due to their unique structural, chemical, and catalytic properties. They possess a three-dimensional framework composed of interconnected silicon (SiO_4) and aluminum (AlO_4) tetrahedra linked through shared oxygen atoms, creating a regular system of channels and cavities of molecular dimensions. These pores enable zeolites to selectively adsorb molecules based on size, shape, and polarity, making them effective molecular sieves, ion exchangers, and heterogeneous catalysts. Since their discovery in 1756 by the Swedish mineralogist Axel Fredrik Cronstedt, zeolites have evolved from naturally occurring minerals into highly engineered synthetic materials with tailored compositions and pore architectures. Today, more than 250 distinct zeolite framework types have been identified, each exhibiting unique structural characteristics and application potential. Natural zeolites such as clinoptilolite, mordenite, and chabazite are widely used in environmental remediation, agriculture, and water purification, whereas synthetic zeolites such as Zeolite A, Zeolite X, Zeolite Y, Beta, and ZSM-5 dominate industrial catalysis, petrochemical processing, gas separation, and detergent manufacturing. The remarkable properties of zeolites—including high surface area, excellent thermal stability, adjustable acidity, high ion-exchange capacity, and exceptional adsorption characteristics—have established them as one of the most versatile classes of functional materials. Recent

advances in nanotechnology, materials engineering, and green chemistry have further expanded their applications into energy storage, carbon dioxide capture, hydrogen production, biomedical engineering, drug delivery, and renewable energy systems.This review provides a detailed discussion of the historical development, crystal chemistry, framework structure, classification, physicochemical properties, synthesis methods, characterization techniques, catalytic mechanisms, adsorption behavior, and diverse applications of natural and synthetic zeolites. The review also examines current research trends, technological challenges, and future prospects for zeolite-based materials in sustainable industrial development.

INTRODUCTION:

The term **zeolite** is derived from the Greek words **"zeo"**, meaning "to boil," and **"lithos,"** meaning "stone." This name was introduced in 1756 by the Swedish mineralogist **Axel Fredrik Cronstedt**, who observed that certain minerals released large quantities of steam when heated. Unlike ordinary minerals, zeolites contain significant amounts of water molecules trapped within their crystal framework. When heated, these water molecules escape without destroying the crystal structure, giving rise to the characteristic boiling appearance. Zeolites belong to the broader family of tectosilicates, or framework silicates. Their crystal structure consists of an interconnected network of silicon-oxygen (SiO_4) and aluminum-oxygen (AlO_4) tetrahedra linked by shared oxygen atoms. The substitution of silicon atoms by aluminum atoms within the framework generates a permanent negative charge that is balanced by exchangeable cations such as sodium (Na^+), potassium (K^+), calcium (Ca^{2+}), or magnesium (Mg^{2+}). These cations are loosely held and can be readily exchanged with other positively charged ions in aqueous solutions, providing zeolites with exceptional ion-exchange properties. The highly ordered arrangement of tetrahedra creates a network of microscopic channels and cavities with diameters ranging approximately from 0.3 to 1.2 nanometers. These pore systems enable selective adsorption of molecules according to their size and geometry. Consequently, zeolites are commonly referred to as **molecular sieves**, as they can separate molecules that differ only slightly in molecular dimensions.

Natural zeolites are primarily formed through hydrothermal alteration of volcanic ash over geological timescales. They are found in volcanic rocks, sedimentary deposits, saline lake sediments, and geothermal environments throughout the world. More than fifty naturally occurring zeolite minerals have been identified, with clinoptilolite, mordenite, chabazite, erionite, and phillipsite being among the most abundant and commercially important. Although natural zeolites possess numerous useful properties, their chemical composition and purity often vary depending on their geological origin. This limitation led to the development of synthetic zeolites during the mid-twentieth century. Synthetic zeolites are manufactured under carefully controlled hydrothermal conditions, allowing precise control over framework composition, pore size, crystal morphology, acidity, and catalytic behavior. The commercialization of synthetic zeolites revolutionized petroleum refining and petrochemical manufacturing by enabling highly efficient catalytic cracking processes.

The diversity of zeolite structures is extraordinary. According to the International Zeolite Association (IZA), over 250 unique framework types have been recognized. Each framework is identified by a three-letter code, such as LTA (Zeolite A), FAU (Zeolite X and Y), MFI (ZSM-5), MOR (Mordenite), and BEA (Beta). Although these frameworks share the same fundamental tetrahedral building blocks, differences in channel geometry, pore size, and framework connectivity produce significantly different physicochemical properties and industrial applications. The performance of a zeolite is strongly influenced by its silicon-to-aluminum (Si/Al) ratio. Zeolites with low Si/Al ratios contain a greater number of aluminum atoms and therefore exhibit higher ion-exchange capacity and stronger hydrophilic behavior. Conversely, high-silica zeolites are more hydrophobic, thermally stable, and resistant to acidic environments, making them particularly suitable for catalytic applications involving organic compounds.

One of the defining characteristics of zeolites is their exceptionally high internal surface area. Although individual crystals may appear compact, their internal pore systems generate surface areas ranging from approximately 300 to over 900 $m^2\ g^{-1}$. This extensive internal surface provides abundant active sites for adsorption, catalysis, and ion exchange, contributing to their outstanding performance in industrial processes. Zeolites have transformed numerous industrial sectors. In petroleum refining, zeolite catalysts are used in fluid catalytic cracking (FCC), hydrocracking, isomerization, alkylation, and dewaxing processes to convert heavy petroleum fractions into valuable fuels such as gasoline, diesel, and jet fuel. In environmental engineering, zeolites remove heavy metals, ammonium ions, radioactive isotopes, dyes, and organic contaminants from wastewater. In gas separation technologies, they selectively adsorb carbon dioxide, nitrogen, sulfur compounds, and water vapor, facilitating purification of natural gas, oxygen production, and carbon capture.

The agricultural sector also benefits significantly from zeolite technology. Natural zeolites improve soil fertility by enhancing water retention, nutrient availability, and fertilizer efficiency while reducing nutrient leaching. They are widely incorporated into animal feed as toxin binders and ammonia adsorbents, improving livestock health and reducing environmental pollution. Biomedical research has recently emerged as another promising field for zeolite applications. Nano-sized zeolites are being investigated as carriers for controlled drug delivery, biosensors, antimicrobial materials, tissue engineering scaffolds, and diagnostic imaging agents. Their biocompatibility, chemical stability, and tunable pore structure make them attractive materials for advanced medical technologies.

Growing environmental concerns and the transition toward sustainable industrial processes have stimulated renewed interest in zeolite research. Scientists are developing hierarchical zeolites that combine microporous and mesoporous structures to improve diffusion rates and catalytic efficiency. Green synthesis methods utilizing industrial wastes such as coal fly ash, rice husk ash, and blast furnace slag are being explored to reduce manufacturing costs and environmental impacts. In addition, zeolites are being investigated for applications in hydrogen storage, carbon capture and utilization (CCU), biomass conversion, renewable fuels, and advanced energy storage systems.

1. HISTORICAL DEVELOPMENT OF ZEOLITES

The development of zeolite science spans more than two and a half centuries, evolving from the study of naturally occurring minerals

to the design of sophisticated synthetic materials that underpin numerous industrial processes. Advances in mineralogy, crystallography, chemistry, materials science, and chemical engineering have collectively transformed zeolites into one of the most important classes of functional porous materials. This section presents the historical evolution of zeolites, highlighting major scientific discoveries and technological milestones.

1.1 Discovery of Zeolites (1756)

The history of zeolites began in **1756**, when the Swedish mineralogist **Axel Fredrik Cronstedt** examined the mineral **stilbite**. During heating experiments, he observed that the mineral released large quantities of water vapor while maintaining its overall crystalline appearance. This unusual phenomenon inspired him to coin the term **"zeolite"**, derived from the Greek words:

- **Zeo (ζέω)** – "to boil"
- **Lithos (λίθος)** – "stone"

Thus, **zeolite literally means "boiling stone."**

Cronstedt recognized that the water released from zeolites was not part of the primary crystal framework but was instead loosely held within internal cavities. This observation became the foundation for understanding the porous nature of zeolites.

Initially, zeolites attracted attention mainly as mineralogical curiosities rather than as technologically useful materials.

1.2 Nineteenth-Century Mineralogical Studies (1800–1900)

Throughout the nineteenth century, mineralogists discovered numerous naturally occurring zeolite minerals in volcanic rocks and hydrothermal deposits. Researchers focused on:

- Mineral identification
- Chemical composition
- Crystal morphology
- Geological occurrence
- Classification

Several important natural zeolite minerals identified during this period include:

- Analcime
- Chabazite
- Natrolite
- Stilbite
- Heulandite
- Phillipsite
- Thomsonite
- Laumontite

These discoveries demonstrated that zeolites were widespread geological minerals formed through hydrothermal alteration of volcanic ash and basaltic rocks.

However, their internal crystal structures remained unknown because modern X-ray crystallography had not yet been developed.

1.2 Early Twentieth Century: Understanding Crystal Structure (1900–1940)

The invention of **X-ray diffraction (XRD)** by **Max von Laue** and the crystallographic work of **William Henry Bragg** and **William Lawrence Bragg** revolutionized mineralogy. Scientists were finally able to investigate the atomic arrangement within zeolite crystals.

Studies revealed that zeolites consist of:

- Silicon-oxygen tetrahedra (SiO_4)
- Aluminum-oxygen tetrahedra (AlO_4)

These tetrahedra are linked through shared oxygen atoms to produce highly ordered three-dimensional frameworks containing

interconnected pores and channels. This discovery explained many of the unusual properties of zeolites, including:

- Reversible dehydration
- Ion exchange
- Molecular adsorption
- High thermal stability

1.3 Richard Barrer and the Birth of Synthetic Zeolites (1940–1955)

The modern era of zeolite science began with the pioneering work of **Richard M. Barrer**, often regarded as the **father of synthetic zeolite chemistry**.

During the 1940s, Barrer demonstrated that zeolites could be synthesized under controlled laboratory conditions through hydrothermal crystallization.

His research established that:

- Temperature influences crystal growth.
- Pressure affects crystallization kinetics.
- Solution chemistry controls framework formation.
- Alkali concentration determines zeolite type.

Barrer successfully synthesized several zeolite structures that closely resembled naturally occurring minerals.

His contributions include:

- Hydrothermal synthesis methods
- Ion-exchange studies
- Gas adsorption mechanisms
- Molecular sieve concepts
- Framework chemistry

These discoveries laid the scientific foundation for the commercial production of synthetic zeolites.

1.4 Commercial Development of Synthetic Zeolites (1950–1970)

During the 1950s, industrial researchers recognized the enormous commercial potential of synthetic zeolites. Scientists at **Union Carbide** developed several commercially important zeolites, including:

Zeolite A (LTA)

Applications:

- Water softening
- Laundry detergents
- Ion exchange
- Gas drying

Zeolite X (FAU)

Applications:

- Gas separation
- Oxygen production
- Air purification

Zeolite Y (FAU)

Applications:

- Petroleum refining
- Catalytic cracking
- Hydrocracking

These synthetic materials possessed:

- Uniform pore sizes
- High purity
- Controlled composition

- Excellent reproducibility

Compared with natural zeolites, synthetic zeolites offered much greater consistency and performance.

1.5 Current Research Trends

Modern research focuses on developing zeolites for emerging technologies, including:

- Carbon dioxide capture and storage (CCS)
- Hydrogen storage
- Renewable fuels
- Biomass conversion
- Drug delivery
- Tissue engineering
- Controlled-release fertilizers
- Fuel cells
- Battery materials
- Water desalination
- Artificial photosynthesis

2. OCCURRENCE, MINERALOGY, AND GEOLOGICAL FORMATION OF NATURAL ZEOLITES

Natural zeolites are among the most abundant crystalline aluminosilicate minerals found in the Earth's crust. They are formed through geological processes involving the interaction of volcanic materials with alkaline groundwater or seawater under low-temperature and low-pressure hydrothermal conditions. Their formation typically requires thousands to millions of years, depending on environmental conditions such as temperature, pressure, pH, and the chemical composition of the surrounding fluids. To date, more than **50 naturally occurring zeolite mineral species** have been identified, although only a limited number are commercially significant due to their abundance and favorable physicochemical properties. Among these, **clinoptilolite** is the most abundant and economically valuable natural zeolite worldwide, accounting for approximately 70–80% of global production. Natural zeolites occur in volcanic tuffs, altered volcanic ash beds, basaltic rocks, sedimentary deposits, saline lake sediments, and geothermal regions. Their unique mineralogical characteristics have made them important raw materials in agriculture, environmental engineering, construction, mining, and water purification.

3. GEOLOGICAL FORMATION OF NATURAL ZEOLITES

Natural zeolites are secondary minerals, meaning they are not formed directly from magma but develop through the alteration of pre-existing volcanic materials. The transformation generally involves chemical reactions between volcanic glass and alkaline aqueous solutions.

The principal mechanisms of zeolite formation include:

(a) Hydrothermal Alteration

Hydrothermal alteration is the most common process responsible for zeolite formation.

In this process:

- Volcanic ash or glass reacts with hot groundwater.
- Temperatures generally range between **50 and 250°C**.
- The reaction may continue for thousands of years.
- Silica and alumina dissolve from volcanic glass and recrystallize into stable zeolite frameworks.

The simplified reaction can be represented as:

Volcanic glass + alkaline solution + water → Zeolite + silica + clay minerals

Hydrothermal alteration commonly produces:

- Clinoptilolite
- Mordenite
- Chabazite
- Phillipsite

(b) Diagenesis

Diagenesis refers to the physical and chemical changes occurring in sediments after deposition.

During burial:

- Volcanic ash layers become compacted.
- Groundwater circulates through the sediments.
- Glass gradually dissolves.
- Zeolite crystals nucleate and grow.

Diagenetic zeolites are commonly associated with:

- Marine sedimentary rocks
- Lacustrine (lake) sediments
- Deep volcanic ash deposits

(c) Burial Metamorphism

As sedimentary rocks are buried deeper, increasing temperature and pressure promote mineral transformations.

Clay minerals and volcanic glass may convert into:

- Analcime
- Laumontite
- Heulandite
- Stilbite

Burial metamorphism generally occurs at temperatures between **100 and 300°C**.

(d) Weathering Processes

In some regions, prolonged weathering of volcanic rocks by alkaline groundwater results in localized zeolite formation.

Although slower than hydrothermal alteration, weathering contributes significantly to zeolite deposits in certain volcanic terrains.

(e)Temperature

Most natural zeolites crystallize between:

- **40–250°C**

Higher temperatures often favor quartz or feldspar formation instead of zeolites.

(f) Pressure

Natural zeolite formation generally occurs under:

- Low pressure
- Shallow crustal conditions

Excessively high pressure transforms zeolites into denser silicate minerals.

(g) Water Availability

Water plays several essential roles:

- Dissolves silica and alumina
- Facilitates ion transport
- Promotes crystal growth
- Stabilizes hydrated frameworks

Without sufficient groundwater, zeolite formation cannot occur.

(h) pH

Most zeolites form in:

- Neutral to alkaline conditions
- pH approximately **7–11**

Highly acidic environments inhibit zeolite crystallization.

4. CHEMICAL COMPOSITION

The availability of:

- Silicon
- Aluminum
- Sodium
- Potassium
- Calcium
- Magnesium

determines which zeolite species will crystallize.

5. MINERALOGICAL CHARACTERISTICS

Zeolites belong to the tectosilicate group of minerals.

Their crystal structures consist of:

- Silicon tetrahedra (SiO_4)
- Aluminumtetrahedra (AlO_4)

joined together by shared oxygen atoms.

Unlike feldspars or quartz, zeolites possess:

- Open framework structures
- Large internal cavities
- Interconnected channels
- Exchangeable cations
- Reversible water adsorption

These structural characteristics distinguish zeolites from most other silicate minerals.

7. MAJOR NATURAL ZEOLITE MINERALS

i. Clinoptilolite

- Most abundant natural zeolite
- High ion-exchange capacity
- Excellent thermal stability
- High selectivity toward ammonium ions
- Good adsorption performance

Applications

- Wastewater treatment
- Soil conditioner
- Animal feed additive
- Water purification
- Heavy metal removal
- Radioactive waste treatment

ii. Mordenite

- High silica content
- Excellent acid resistance
- One-dimensional pore system
- High thermal stability

Applications

- Catalytic cracking
- Hydrocracking
- Gas separation
- Petroleum refining

iii. Chabazite

- Three-dimensional pore structure
- High CO_2 adsorption capacity
- Excellent ion-exchange behavior

Applications

- Carbon dioxide capture
- Gas separation
- Wastewater treatment
- Catalysis

iv. Analcime

- Nearly cubic crystal symmetry
- Relatively dense structure
- Lower ion-exchange capacity

Applications

- Construction materials

- Ceramic production
- Geological indicators

v. Heulandite

- High calcium content
- Moderate adsorption capacity
- Good thermal stability

Applications

- Soil improvement
- Water purification
- Ion exchange

vi. Stilbite

Stilbite was the first zeolite studied by Cronstedt.

- Needle-like crystals
- High water content
- Attractive crystal morphology

Applications are mainly mineralogical and ornamental, with limited industrial use.

vii. Phillipsite

- Rich in potassium
- High cation exchange capacity
- Forms in volcanic tuffs

Applications:

- Agriculture
- Wastewater treatment
- Heavy metal removal

viii. Erionite

Erionite possesses excellent adsorption properties but is **not used commercially** because inhalation of erionitefibers has been associated with serious health risks, including an increased risk of mesothelioma. Appropriate occupational health precautions are therefore essential when erionite-bearing materials are encountered.

8. GLOBAL DISTRIBUTION OF NATURAL ZEOLITES

Natural zeolite deposits are widely distributed across the world, especially in regions with extensive volcanic activity.

Major producing countries include:

Country	Major Zeolite Deposits
China	Clinoptilolite, Mordenite
Turkey	Clinoptilolite
United States	Clinoptilolite, Chabazite
Japan	Clinoptilolite, Mordenite
Slovakia	Clinoptilolite
Hungary	Clinoptilolite
Cuba	Clinoptilolite
Italy	Chabazite
South Korea	Clinoptilolite
India	Clinoptilolite and associated volcanic tuff deposits

China and Turkey are among the world's leading producers of natural zeolites due to their extensive volcanic sedimentary formations.

9. NATURAL VS SYNTHETIC ZEOLITES

Property	Natural Zeolites	Synthetic Zeolites
Source	Geological deposits	Laboratory synthesis
Purity	Variable	High
Cost	Low	Higher
Composition	Naturally variable	Precisely controlled
Crystal Size	Variable	Uniform
Framework Types	~50 natural species	250+ framework types
Industrial Performance	Moderate	Highly optimized
Availability	Deposit dependent	Manufactured on demand

Natural zeolites are generally preferred for low-cost, large-scale applications such as agriculture and environmental remediation, whereas synthetic zeolites are favored for catalysis and advanced separation processes because of their uniformity and tailored properties.

10. ECONOMIC IMPORTANCE

Natural zeolite mining has become a significant industry due to the growing demand for sustainable and environmentally friendly materials.

Major commercial sectors include:

- Water treatment
- Wastewater treatment
- Agriculture
- Animal husbandry
- Aquaculture
- Construction materials
- Cement additives
- Gas purification
- Odor control
- Environmental remediation

The increasing emphasis on circular economy practices has further enhanced the value of natural zeolites, particularly for recycling nutrients, removing pollutants, and converting industrial by-products into useful materials.

SUMMARY

Natural zeolites are secondary aluminosilicate minerals formed primarily through the hydrothermal and diagenetic alteration of volcanic materials under alkaline conditions. Their unique crystalline framework, high ion-exchange capacity, reversible hydration behavior, and molecular sieving properties make them valuable across numerous industrial, environmental, and agricultural applications. Among the many naturally occurring zeolite species, clinoptilolite is the most abundant and economically significant. Although natural zeolites exhibit variable composition and purity, they remain an inexpensive and sustainable source of functional porous materials. Their widespread occurrence, ease of mining, and versatility continue to support growing global demand, while synthetic zeolites complement them in applications requiring precise structural control.

REFERENCES

Breck, D. W. (1974). *Zeolite Molecular Sieves: Structure, Chemistry, and Use*. John Wiley & Sons.

Barrer, R. M. (1978). *Zeolites and Clay Minerals as Sorbents and Molecular Sieves*. Academic Press.

Čejka, J., Corma, A., & Zones, S. I. (2010). *Zeolites and Catalysis: Synthesis, Reactions and Applications*. Wiley-VCH.

Cundy, C. S., & Cox, P. A. (2003). "The hydrothermal synthesis of zeolites: History and development from the earliest days to the present time." *Microporous and Mesoporous Materials*, **82**, 1–78.

International Zeolite Association (IZA). *Atlas of Zeolite Framework Types*.